TEST REPORT

Report No.: 66.430.26.3090.01

Dated: 2026-06-11

中国认可
国际互认
检测
TESTING
CNAS L7038

Applicant:	Treck S.A.
Address:	Avenida Santa Rosa5220, San Joaquin, Santiago, Chile
Contact Person:	Andres
Sample Submitted:	The Sample(s) and Its (Their) Information(s) Was (Were) Submitted by Applicant and Identified. A. Navy waist belt - 1 piece
Sample Description:	88% Cotton 12% Nylon, Woven, Canvas, 9.5oz Cinturón Ignífugo Absolute Fire NFPA Azul Marino
Colour:	Navy
Style No.:	147-20-010
Sample Received Date:	2026-06-05
Date of Testing:	2026-06-09 to 2026-06-10
Test Result(s):	Refer to the Section 3 and 4

Note:
(1) Each order is subject to acceptance of our General Terms and Conditions and the TÜV SÜD Testing, Certification, Validation and Verification Regulation, in the version valid at the time the contract is concluded. For full version of above both documents, please visit the link to view.
(2) The results in this report are relevant only to the sample(s) tested.
(3) The test report shall not be reproduced except in full without the written approval of the laboratory.
(4) Disclaimer Measurement Uncertainty:
Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019 or CNAS-GL015:2022.
(5) The testing report without CMA stamp is not legally binding and could only be used as internal reference material for the applicant. It shall not be provided as a notarial certification.

1. Test Sample Photo(s)



Sample A

2. Identification of The Test Subject

Sample	Description	Remark
001	Navy fabric (body)	Finished Product (A)

3. Conclusion

No.	Test Parameter(s)	Conclusion
1.	Standard Test Method for Flame Resistance of Textiles (Vertical Test) (ASTM D6413/D6413M-15)	Pass
2.	Standard Test Method for Flame Resistance of Textiles (Vertical Test) (ASTM D6413/D6413M-22)	Pass

Note: Pass= Meet Requirement
#= No Comment
N/A = Not Applicable
Fail= Below Requirement
- = Did Not Perform

Remark: (1) Samples are tested as received.

TÜV SÜD Certification and Testing (China) Co., Ltd. Xiamen Branch

Reviewed by:

Stacey Yang
Softlines Department

Approved by:

Damon Zheng
Softlines Department

4. Test Results

4.1 Standard Test Method for Flame Resistance of Textiles (Vertical Test) (ASTM D6413/D6413M-15)

Ignition: 12 ± 0.2s
Gas: Methane

Sample	Parameters		Results				ASTM F1506-22 Requirement	Conclusion
			Afterflame (s)	Afterglow (s)	Dripping / Melting	Char Length (mm)		
001	Widthwise	1	0.0	-	#1	84	*	Pass
		2	0.0	-	#1	90		
		3	0.0	-	#1	96		
		4	0.0	-	#1	87		
		5	0.0	-	#1	87		
	Mean		0.0	-	-	90		

Remark: #1= Melting or dripping didn't occur.

*=

Afterflame	Afterflame time shall be ≤ 2 s.
Dripping/Melting	Shall not melt and drip.
Char length	Not exceed 152 mm

4.2 Standard Test Method for Flame Resistance of Textiles (Vertical Test) (ASTM D6413/D6413M-22)

Ignition: 12 ± 0.2s
Gas: Methane

Sample	Parameters		Results				NFPA2112-2023 Requirement	Conclusion
			Afterflame (s)	Afterglow (s)	Dripping / Melting	Char Length (mm)		
001	Widthwise	1	0.0	-	#1	84	*	Pass
		2	0.0	-	#1	90		
		3	0.0	-	#1	96		
		4	0.0	-	#1	87		
		5	0.0	-	#1	87		
	Mean		0.0	-	-	90		

Remark: #1= Melting or dripping didn't occur.

*=

Afterflame	Afterflame time shall be ≤ 2 s.
Dripping/Melting	Shall not melt and drip.
Char length	Not more than 100 mm

-- END OF THE TEST REPORT –

The sample as below was not tested, and the picture was attached in the report only for the client's reference as per client's request.

